

European Oak

Family Name: Fagaceae

Latin Name: Quercus Robur

Origin: UK & Europe

Strength Class: D30

Weight: Approx 700 kg/m³

Durability: Heartwood is Durable

Description: Colour varies from tan to biscuit, usually straight grained

but irregular or cross-grained material can occur.

Characteristic silver grain figure on quartered surfaces.

Medium to coarse texture.

Mechanical Very good steam bending classification. Dries very slowly

Properties: with a tendancy to split and check. Medium movement in

service.

Main Uses: Blocks Sleepers

Wedges Boat Building – English Oak

Beams Dock & Harbour – English Oak
Bogmats Garden Furniture – English Oak

Furniture Joinery

Flooring Sleepers