



Larch

Family Name: Pinaceae

Latin Name: Larix Decidua

Origin: Central Europe

Strength Class: C24

Weight: Approx 575 kg/m³

Durability: Moderately Durable

Description: Colour varies from yellow to a medium reddish brown. The grain is generally straight and has a fine texture.

Mechanical Properties: Difficult to dry due to high resin content. Should be dried slowly to avoid checking. Low shock resistance.

Main Uses:	Veneer	Boat Building
	Utility Poles	Construction Lumbar
	Fence Posts	Bridge Construction
	Flooring	Decking
	Exterior Cladding	Interior Panelling